

Technical Data Sheet

Product	PF51 serie colore						
Description	Solvent-based concentrated dyes						
Code/Color	CODE	COLOR					
	PF51		Yellow				
	PF52		Vivid yellow				
	PF54		Orange				
	PF55	Red					
	PF57	Violet					
	PF58	Blue					
	PF5V	Green					
	PF59	Black					
Woods for which the product is suitable	Non resinous softwood						
	Dark color hardwood						
	Light color hardwood						
Substrates for which the product is suitable	Veneer						
	Solid wood						
Chemical-physical Prop	erties						
CODE	Density (Kg/l)	Density (Ib/US gal)			Solid content %		
PF51	0,965 ± 0,030	8,1	±	0,3	4,5	±	2
PF52	0,967 ± 0,030	8,1	±	0,3	10,1	±	2
PF54	0,950 ± 0,030	7,9	±	0,3	4,5	±	2
PF55	0,960 ± 0,030	8,0	±	0,3	10,1	±	2
PF57	0,968 ± 0,030	8,1	±	0,3	4,5	±	2
PF58	0,961 ± 0,030	8,0	±	0,3	10,1	±	2
PF5V	0,966 ± 0,030	8,1	±	0,3	10,2	±	2
PF59	0,973 ± 0,030	8,1	±	0,3	24,0	±	2
	Viscosity (EN ISO 2431) ISO 3 cup		23	±	2		
USAGE INDICATIONS			1				
The product, after carefu	ul mixing, is ready to use						
Shelf life	18 months after production PF52 may create problems on tannin rich woods (chestnut, oak, softwood, etc.) or if it is						
SPECIFIC WARNINGS	PF52 may create problems on tannin ric overcoated with acid-components coatir		iestnut, oa	ak, softwood	l, etc.) or i	f it is	

IVM Chemicals srl – International Wood Coating Division - 27020 Parona (PV), V.le della Stazione 3 - tel. +39 0384 25 44.1 - fax +39 0384 252 054

Sede sociale: 20123 Milano, Via Tasso 10 - capitale sociale i.v. €10.000.000 codice fiscale, registro imprese C.C.I.A.A n. 02170230342 - REA n. 1657837- Partita IVA 13472030157 ilva@ivmchemicals.com - www.ilva.it



WARNINGS

In a coating process with professional products:

- besides the product quality, the final result also depends on numerous other variables, such as environmental conditions; homogeneity in the quality of the support; the constancy of the application cycle; the plants performance; the proper use of the product, etc.
- in the process of industrial coating a certain waste of product is to be considered normal and therefore not attributable to product quality
- The final colour is influenced by the quality and preparation of the support and the conditions of application, for this reason it is essential to check in advance the result in terms of final use

Our Company cannot ensure the control of the coating process carried out by the user. We cannot, therefore, take on any responsibility for the final result achieved through the use of our products.

On the other hand, we guarantee the consistency of the chemical and physical characteristics of the product indicated in the relevant Technical Data Sheet, pledging to replace it if it does not correspond to the declared features Data on the chemical and physical characteristics of the product are recorded at 20°C / 68°F and 70% R.U.

For best results, the optimum conditions of application are:

- Ambient temperature between 18 and 22°C (64 72 °F)
- ambient relative humidity between 65 and 70%
- support humidity between 8 and 14%

The conditions to be observed scrupulously are:

- Water-based products are particularly sensitive to storage conditions: temperatures below 5 °C / 41°F and above 35 °C / 95°F may affect the product, characteristics, making it unusable. For this reason, a waterbased product should be stored indoors at temperatures not below 5 °C and not above 35 °C / 95°F, in a properly ventilated place, not exposed to solar radiation
- A solvent-based product should be stored indoors at temperatures not below 0 °C / 32°F or above 35 °C / 95°F, in a properly ventilated place, not exposed to solar radiation
- In case a storage temperature below 15 °C / 59°Fis detected, the product should be restored at the optimal temperature of 18-22°C (64-72°F). before use
- Always shake the products well before use
- Before use, always shake well the product mixed with any other components such as catalysts, accelerators, thinners
- The application must not take place at a temperature lower than 15 °C / 59°F or above 30°C / 86°F
- The drying should not take place at a temperature below 15 °C / 59°F
- The ambient relative humidity during drying should be between 50% and 70%
- To decant paints, exclusively use containers made of suitable material, such as polyethylene and stainless steel
- After use, we recommend that you always close the can carefully

The end result of the coating cycle is the sole responsibility of the users, who must make sure that the product matches their needs and that environmental conditions, application or media specifications do not require substantial changes of use

It is the user's responsibility:

- Adhere to the conditions indicated above
- comply with the rules of hygiene and safety during product application, according to the descriptions given in the safety data sheets
- for solvent-based products spark-proof equipment should be used
- It is forbidden to smoke while using the product

At the bottom of each sheet there is a date of validity

The Company invites you to check with their staff that the product data sheet in your possession is the most updated, since the characteristics of the products are subject to adjustments over time For more information, please contact (see below):

Issue date: 2015-07

Rev.: 1

IVM Chemicals srl – International Wood Coating Division - 27020 Parona (PV), V.le della Stazione 3 - tel. +39 0384 25 44.1 - fax +39 0384 252 054